

## TECHNICAL LEAFLET



Useful information on

## Inspection of insulating glass

In general, when checking for defects, the view through the pane, i.e. looking at the background, is relevant, and not the top-down view. Complaints must not be specifically marked.

The evaluation is performed perpendicular to the glass surface from the side of primary use at a distance of 3 m.

Where possible, the assessment should be carried out in daylight without direct sunlight (diffuse daylight) or artificial light to highlight phenomena.

The insulating glass is inspected according to SIGAB guideline 006 Visual evaluation of glass in construction.

